

AMENDMENTS TO THE CLAIMS:

This listing of Claims will replace all prior versions, and listings, of Claims in the application:

LISTING OF CLAIMS:

1 to 3. (Canceled).

4. (Currently Amended) A supported catalyst suitable for use as a cathode of direct methanol fuel cells, comprising:

an electroconductive, porous carrier having micropores; and

catalyst particles positioned in the pores of the carrier comprising an alloy selected from the group consisting of Cd and Au; Cd and Ag; Cd and Cu; Cd and Ni; ~~Cd and Pd~~; Cd and Pt; Zn and Au; Zn and Ag; Zn and Cu; Zn and Ni; ~~Cu and Pd~~; and Ag and Pt, wherein the alloy has a stronger oxygen-binding force than platinum or a weaker hydrogen-binding force than platinum.

5 to 12. (Canceled).

13. (Previously Presented) The supported catalyst according to claim 4, wherein the alloy has a stronger oxygen-binding force than platinum and a weaker hydrogen-binding force than platinum.

14. (Canceled).

15. (Currently Amended) The supported catalyst according to claim 4, wherein the carrier is ~~activated carbon~~, graphite, mesoporous carbon powder or carbon nano tube.

16. (Currently Amended) A direct methanol fuel cell comprising:
a cathode;
an anode; and

an electrolyte membrane being placed between the cathode and the anode, wherein the cathode comprises the supported catalyst which comprises an electroconductive, porous carrier having micropores; and

catalyst particles positioned in the pores of the carrier comprising an alloy selected from the group consisting of Cd and Au; Cd and Ag; Cd and Cu; Cd and Ni; ~~Cd and Pd~~; Cd and Pt; Zn and Au; Zn and Ag; Zn and Cu; Zn and Ni; ~~Cu and Pd~~; and Ag and Pt, wherein the alloy has a stronger oxygen-binding force than platinum or a weaker hydrogen-binding force than platinum.

17. (Previously Presented) The fuel cell according to claim 16, wherein the alloy has a stronger oxygen-binding force than platinum and a weaker hydrogen-binding force than platinum.

18. (Canceled).

19 to 21. (Canceled).

22. (Previously Presented) The supported catalyst according to claim 4, wherein the oxygen-binding energy is at least 4.5 eV and/or the hydrogen-binding energy is at most 2.5 eV.

23. (Currently Amended) The supported catalyst according to claim 4, wherein the alloy comprises three or more metals, wherein the alloy further comprises Co, Ni, Rh, [[Pd]], Pt, Cu, Ag, Au, Zn and/or Cd.

24. (Previously Presented) The fuel cell according to claim 16, wherein the oxygen-binding energy is at least 4.5 eV and/or the hydrogen-binding energy is at most 2.5 eV.

25. (Currently Amended) The fuel cell according to claim 16, wherein the alloy comprises three or more metals, wherein the alloy further comprises Co, Ni, Rh, [[Pd]], Pt, Cu, Ag, Au, Zn and/or Cd.

26 to 27. (Canceled).

28. (New) A direct methanol fuel cell comprising:

a cathode;

an anode; and

an electrolyte membrane being placed between the cathode and the anode, wherein the cathode comprises the supported catalyst which comprises an electroconductive, porous carrier having micropores selected from the group consisting of graphite, mesoporous carbon powder, and carbon nano tube; and

catalyst particles positioned in the pores of the carrier comprising an alloy selected from the group consist of Cd and Au; Cd and Ag; Cd and Cu; Cd and Ni; Cd and Pt; Zn and Au; Zn and Ag; Zn and Cu; Zn and Ni; and Ag and Pt, wherein the alloy has a stronger oxygen-binding force than platinum or a weaker hydrogen-binding force than platinum.